

520 Eagleton Downs Drive - D Pineville, NC 28134 O: 704.405.2550 F: 704.543.9772 www.americanflamecoat.com

Client: ELITIS INC. 21-07 41<sup>st</sup> AVENUE LON ISLAND CITY, NY 11101

Test Report No: 119254 PO# ELITIS – CMO WLI 01 Date: November 3, 2024

The sample submitted by the client as: ELITIS INC. – CMO ESSENCE NATURELLE - CMO WLI 01 (ADHERED)

**DATE OF RECEIPT: 09.17.2024** 

**TESTING PERIOD: 17 DAYS** 

TEST REQUESTED: The submitted sample was tested for flammability in Accordance with the procedures outlined in ASTM E-84-24a.

**SIGNED** 

Many





520 Eagleton Downs Drive - D Pineville, NC 28134 O: 704.405.2550 F: 704.543.9772 www.americanflamecoat.com

Client: ELITIS INC.

21-07 41st AVENUE

LON ISLAND CITY, NY 11101

# **INTRODUCTION:**

This report presents test results of Flame Spread and Smoke Developed Value per ASTM E-84-24a. The report also includes Material Identification, Method of Preparation, Mounting and Conditioning of the specimens.

The tests were performed in accordance with the specifications set forth in ASTM E-84-24a, Standard Test Method for Surface Burning Characteristics of Building Materials, both as to equipment and test procedures. This test procedure is similar to UL-723, ANSI NO. 2.5, NFPA No. 255 and UBC 42-1.

The test results cover two parameters: Flame Spread and Smoke Developed Values during the 10-minute fire exposure. Inorganic cement board and red oak flooring are used as comparative standards, and their responses are assigned arbitrary values of 0 and 100 respectively.

### **PREPARATION AND CONDITIONING:**

The test sample identified as ELITIS INC. - CMO ESSENCE NATURELLE - CMO WLI 01 - (ADHERED) was prepared by adhering the material to 5/8" Type X gypsum board, glued using Roman – PRO-774 Clay Strippable Wallcovering Adhesive. This method of sample preparation is described in ASTM E2404-17, standard practice.

### **TEST PROCEDURE:** Adhered

The tunnel was thoroughly pre-heated by burning natural gas. When the brick temperature, sensed by a floor thermocouple, had reached the prescribed 105 Fahrenheit +/- 5 Fahrenheit level, the sample was inserted in the tunnel and a test conducted in accordance with the standard ASTM E-84-24a procedures.

The operation of the tunnel was checked by performing a 10-minute test with inorganic board of the day of the test.

This test sample \*meets the A.S.T.M. E-84 Standard

This test sample \*meets the N.F.P.A. LIFE SAFETY CODE 101.



520 Eagleton Downs Drive - D Pineville, NC 28134 O: 704.405.2550

F: 704.543.9772

www.americanflamecoat.com

Client: ELITIS INC.

21-07 41st AVENUE

LON ISLAND CITY, NY 11101

# **TEST RESULTS:**

The test results calculated in accordance with ASTM E-84-24a for Flame Spread and Smoke Developed Values are as follows:

Test Specimen: ELITIS INC. – CMO ESSENCE NATURELLE - CMO WLI 01 (ADHERED)

Flame Index = 50 Smoke Developed Value = 40

Observation: Tested Fabric Meets the Requirements for ASTME-84-24

### Rating: Class B


The National Fire Protection Association Life Safety Code 101, Section 6-5.3, "Interior Wall and Ceiling Finish Classification", has a means of classifying materials with respect to Flame Spread and Smoke Developed when tested in accordance with NFPA 255, "Method of Test of Surface Burning Characteristics of Building Materials", (ASTM E-84-24a)

The classifications are as follows:


Class A Interior Wall & Ceiling Finish:  Class B Interior Wall & Ceiling Finish:	Flame Spread-	0-25
	Smoke Developed-	0-450
	Flame Spread-	26-75
	Smoke Developed-	0-450

Client: Report#: Sample:

ELITIS INC. 119254 CMO ESSENCE NATURELLE - CMO WLI 01 - (ADHERED)



ELITIS INC. 119254 CMO ESSENCE NATURELLE - CMO WLI 01 - (ADHERED) Client: Report#: Sample:



Client:

Report#: Sample:

ELITIS INC. 119254 CMO ESSENCE NATURELLE - CMO WLI 01 - (ADHERED)

